

ZO2200

2023.04.03

SPECIFICATIONS

- ▶ Chemical formula: ZrO₂
- ▶ Chemical name: Zirconia
- ▶ Apperance: Dense sintered zirconia
- ▶ Main characteristics: High mechanical strength, excellent wear resistance, good surface finish, high fracture toughness
- ▶ Main applications: Pump parts, dies, knives, cutting blades, spikes, club faces, scissors
- ▶ Colour: Yellow

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density	[g/cm ³]	JIS R 1634	5.6
Water absorption	[%]	JIS C 2141	0
Vickers hardness HV9.807N	[GPa]	JIS R 1610	10.7
Flexural strength 3 P.B.	[MPa]	JIS R 1601	750
Compressive strength	[MPa]	JIS R 1608	-
Young's modulus of elasticity	[GPa]	JIS R 1602	200
Poisson's ratio	[ν]	JIS R 1602	0.31
Fracture toughness (SEPB)	[MPa*m ^{0.5}]	JIS R 1607	7 ~ 8
Coefficient of linear thermal expansion	40 - 400 °C	[$\times 10^{-6}$ /K]	10
	40 - 800 °C	[$\times 10^{-6}$ /K]	10.5
Thermal conductivity	[W/(m*K)]	JIS R 1611	3
Specific heat capacity	[J/(g*K)]	JIS R 1611	0.46
Thermal shock temperature difference	[°C]	JIS R 1648	450
Dielectric strength	[kV/mm]	JIS C 2141	13
Volume resistivity	20 °C		>10 ¹⁴
	300 °C	[Ω*cm]	10 ⁶
	500 °C	[Ω*cm]	10 ⁴
Dielectric constant	-	JIS C 2141	28
Dielectric loss angle	[$\times 10^{-4}$]	JIS C 2141	17
Loss factor	[$\times 10^{-4}$]	JIS C 2141	476

The values are typical material properties and may vary according to products configuration and manufacturing process.
 For more details, please feel free to contact us.

KYOCERA Fineceramics Europe GmbH

 E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de