

## AO4450 ( $\geq 90\%$ )

2023.04.03

### SPECIFICATIONS

▶ Chemical formula:	Al <sub>2</sub> O <sub>3</sub>
▶ Chemical name:	Aluminium oxide
▶ Apperance:	Dense sintered aluminum oxide
▶ Main characteristics:	High mechanical strength, high temperature resistance, high frequency insulation, high chemical resistance, light intercepting, high heat dissipation
▶ Main applications:	IC packages
▶ Colour:	Dark brown

### MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

<b>Density</b>		[g/cm <sup>3</sup> ]	JIS R 1634	3.8
<b>Water absorption</b>		[%]	JIS C 2141	0
<b>Vickers hardness HV9.807N</b>		[GPa]	JIS R 1610	12.7
<b>Flexural strength 3 P.B.</b>		[MPa]	JIS R 1601	320
<b>Compressive strength</b>		[MPa]	JIS R 1608	-
<b>Young's modulus of elasticity</b>		[GPa]	JIS R 1602	320
<b>Poisson's ratio</b>		[ $\nu$ ]	JIS R 1602	0.23
<b>Fracture toughness (SEPB)</b>		[MPa*m <sup>0.5</sup> ]	JIS R 1607	-
<b>Coefficient of linear thermal expansion</b>	40 - 400 °C	[ $\times 10^{-6}$ /K]	JIS R 1618	7.3
	40 - 800 °C	[ $\times 10^{-6}$ /K]		8.1
<b>Thermal conductivity</b>		[W/(m*K)]	JIS R 1611	12
<b>Specific heat capacity</b>		[J/(g*K)]	JIS R 1611	0.75
<b>Thermal shock temperature difference</b>		[°C]	JIS R 1648	-
<b>Dielectric strength</b>		[kV/mm]	JIS C 2141	12
<b>Volume resistivity</b>	20 °C	[ $\Omega^*$ cm]	JIS C 2141	$10^{11}$
	300 °C	[ $\Omega^*$ cm]		$10^7$
	500 °C	[ $\Omega^*$ cm]		$10^5$
<b>Dielectric constant</b>		-	JIS C 2141	9.8
<b>Dielectric loss angle</b>		[ $\times 10^{-4}$ ]	JIS C 2141	20
<b>Loss factor</b>		[ $\times 10^{-4}$ ]	JIS C 2141	190

The values are typical material properties and may vary according to products configuration and manufacturing process.  
For more details, please feel free to contact us.

**KYOCERA Fineceramics Europe GmbH**

E-Mail: [info@kyocera-fineceramics.de](mailto:info@kyocera-fineceramics.de) · [www.kyocera-fineceramics.de](http://www.kyocera-fineceramics.de)

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.