

## SN2400

2023.04.03

### SPECIFICATIONS

▶ Chemical formula:	$\text{Si}_3\text{N}_4$
▶ Chemical name:	Silicon nitride
▶ Apperance:	Dense sintered silicon nitride
▶ Main characteristics:	High temperature strength, wear resistant ,excellent thermal shock resistance, light weight, high strength, high temperature durability
▶ Main applications:	Anti wear liner, powder equipment, molten metal parts, metal forming tool
▶ Colour:	Black

### MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

<b>Density</b>		[g/cm <sup>3</sup> ]	JIS R 1634	3.3
<b>Water absorption</b>		[%]	JIS C 2141	0
<b>Vickers hardness HV9.807N</b>		[GPa]	JIS R 1610	14.0
<b>Flexural strength 3 P.B.</b>		[MPa]	JIS R 1601	1,020
<b>Compressive strength</b>		[MPa]	JIS R 1608	-
<b>Young's modulus of elasticity</b>		[GPa]	JIS R 1602	300
<b>Poisson's ratio</b>		[ $\nu$ ]	JIS R 1602	0.28
<b>Fracture toughness (SEPB)</b>		[MPa*m <sup>0.5</sup> ]	JIS R 1607	7
<b>Coefficient of linear thermal expansion</b>	40 - 400 °C			2.8
	40 - 800 °C	[ $\times 10^{-6}/\text{K}$ ]	JIS R 1618	3.3
<b>Thermal conductivity</b>		[W/(m*K)]	JIS R 1611	27
<b>Specific heat capacity</b>		[J/(g*K)]	JIS R 1611	0.65
<b>Thermal shock temperature difference</b>		[°C]	JIS R 1648	800
<b>Dielectric strength</b>		[kV/mm]	JIS C 2141	13
<b>Volume resistivity</b>	20 °C			>10 <sup>14</sup>
	300 °C	[ $\Omega \cdot \text{cm}$ ]	JIS C 2141	10 <sup>12</sup>
	500 °C			10 <sup>10</sup>
<b>Dielectric constant</b>		-	JIS C 2141	9.6
<b>Dielectric loss angle</b>		[ $\times 10^{-4}$ ]	JIS C 2141	19
<b>Loss factor</b>		[ $\times 10^{-4}$ ]	JIS C 2141	-

The values are typical material properties and may vary according to products configuration and manufacturing process.  
For more details, please feel free to contact us.

**KYOCERA Fineceramics Europe GmbH**

E-Mail: [info@kyocera-fineceramics.de](mailto:info@kyocera-fineceramics.de) · [www.kyocera-fineceramics.de](http://www.kyocera-fineceramics.de)