

AO479M/G ($\geq 99.5\%$)

2023.04.03

SPECIFICATIONS

▶ Chemical formula:	Al ₂ O ₃
▶ Chemical name:	Aluminium oxide
▶ Apperance:	Dense sintered aluminum oxide
▶ Main characteristics:	High mechanical strength, high temperature resistance, high frequency insulation, high chemical resistance
▶ Main applications:	Wear resistant parts, chemically resitant parts, semiconductor processing equipment parts
▶ Colour:	Ivory

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density		[g/cm ³]	JIS R 1634	3.9
Water absorption		[%]	JIS C 2141	0
Vickers hardness HV9.807N		[GPa]	JIS R 1610	15.7
Flexural strength 3 P.B.		[MPa]	JIS R 1601	370
Compressive strength		[MPa]	JIS R 1608	-
Young's modulus of elasticity		[GPa]	JIS R 1602	370
Poisson's ratio		[ν]	JIS R 1602	0.23
Fracture toughness (SEPB)		[MPa*m ^{0.5}]	JIS R 1607	-
Coefficient of linear thermal expansion	40 - 400 °C	[$\times 10^{-6}$ /K]	JIS R 1618	7.2
	40 - 800 °C	[$\times 10^{-6}$ /K]		8.0
Thermal conductivity		[W/(m*K)]	JIS R 1611	32
Specific heat capacity		[J/(g*K)]	JIS R 1611	0.78
Thermal shock temperature difference		[°C]	JIS R 1648	-
Dielectric strength		[kV/mm]	JIS C 2141	15
Volume resistivity	20 °C		JIS C 2141	>10 ¹⁴
	300 °C	[Ω*cm]		10 ¹³
	500 °C	[Ω*cm]		10 ¹⁰
Dielectric constant		-	JIS C 2141	9.9
Dielectric loss angle		[$\times 10^{-4}$]	JIS C 2141	1
Loss factor		[$\times 10^{-4}$]	JIS C 2141	10

The values are typical material properties and may vary according to products configuration and manufacturing process.
For more details, please feel free to contact us.

KYOCERA Fineceramics Europe GmbH

E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.