

STARCERAM® N 7000, 7015

2023.11.24

SPECIFICATIONS

- ▶ Chemical formula: Si_3N_4
- ▶ Chemical name: Silicon nitride
- ▶ Characteristic: Sintered silicon nitride
- ▶ Description of product: Parts made of silicon nitride
- ▶ Colour: Light grey to dark grey

CHEMICAL CHARACTERISTICS (TYP.)

		N 7000	N 7015
Si_3N_4 (incl. Al_2O_3 ; Y_2O_3)	[wt%]	> 99	> 99

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

		N 7000	N 7015
Density	[g/cm ³]	3.22	3.23
Open porosity	[vol%]	0	0
Flexural strength $\sigma_{b4,m}$ (RT) ¹	[MPa]	800	950
Weibull modulus (RT)	[-]	>15	>15
Poisson's ratio	[-]	0.3	0.3
Young's modulus (RT)	[GPa]	300	300
Fracture toughness ²	[MPa $\sqrt{\text{m}}$]	6.7	5.7
Thermal conductivity (RT)	[W/mK]	20	20
Thermal expansion CTE (RT-1,000°C)	[x10 ⁻⁶ /K]	3.4	3.3
Hardness (HV10)	[GPa]	15	15
Thermal shock resistance ³	[K]	450	505
Max. working temperature	[°C]	1000	1200

¹ 4-point-bending 40/20 mm

² SEVNB method

³ DIN EN ISO 60672-2:2000-10



STARCERAM® N 7000, 7015

2023.11.24

PACKAGING

StarCeram® N 7000 and 7015 products are individually packed, depending on size.
Packaging acc. to transport regulations.

STORAGE & HANDLING

Handle with care! Ceramic products may break if not treated properly. Storage and handling are subject to the rules and regulations in the country of use.

HAZARDS IDENTIFICATION IN ADVERTISING (REGULATION (EC) NO 1272/2008 ARTICLE 48)

none

DOCUMENTATION

An inspection document in accordance with EN 10204 is supplied with every shipment.

The information contained herein, and in particular the recommendations relating to the application and end-use of our products, are given in good faith based on our current knowledge and experience. The information do not constitute a guarantee with respect to properties of the products. Since we have no control over the application modalities, no guarantee is granted with respect to merchantability or fitness for a particular purpose. It is your sole responsibility to validate the suitability and completeness for your own use. We therefore recommend to always perform a test according to specific circumstances. Any liability in respect of the information in this data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in case of death or personal injury, intent or gross negligence and under any applicable mandatory product liability law. Technical data are subject to change without notice. The newest version of the technical data sheet replaces all preceding versions. The trademarks, trade names, logos and other designations of origin contained in this data sheet are registered and unregistered intellectual property rights of KYOCERA Fineceramics Europe GmbH. It is forbidden to copy or use information from this data sheet in whole or in part, especially in dealings with third parties.

KYOCERA Fineceramics Europe GmbH

E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.